




TRInternational, Inc.
Seattle Tower, 21st Floor
1218 Third Avenue
Seattle, WA 98101 U.S.A.
Phone: (206) 505-3500
Fax: (206) 505-3501
Web: <http://www.tritrading.com>

Certificate of Analysis Resin YD-128

TRI Ref#: 14250
Lot #: 1L 1206105
Ship Date: 4/21/06

<u>Test Item</u>	<u>Unit</u>	<u>Test Method</u>	<u>Specification</u>	<u>Result</u>
EPOXY EQUIVALENT WEIGHT.	g/eq	DIN16945/4.15B(89) TEC-AS-C-002	184 ~ 189	186.6
COLOR	Gardner	ASTM D-1544(89) ASTM D-1209 (88) TEC-AS-P-006	MAX 0.5 / -	0.2/35
VISCOSITY @25° C	cPs	JIS K 7233(86)	12,000 ~ 14,500	12,500
HYDROLYSABLE CHLORINE	wt%	ASTM D-1726(87) TEC-AS-C-007	MAX 0.1	0.040



Quality - Responsibility - Stewardship

