




TRInternational, Inc.
Seattle Tower, 21st Floor
1218 Third Avenue
Seattle, WA 98101 U.S.A.
Phone: (206) 505-3500
Fax: (206) 505-3501
Web: <http://www.tritrading.com>

Certificate of Analysis

Resin YD 801 x 75

TRI Ref#: 14184
Lot #: 2L 2606001
Ship Date: 3/18/06

<u>Test Item</u>	<u>Unit</u>	<u>Test Method</u>	<u>Specification</u>	<u>Result</u>
EPOXY EQUIVALENT WEIGHT.	g/eq	DIN16945/4.15B(89) TEC-AS-C-002	440 ~ 500	468.9
COLOR	Gardner	ASTM D-1544(89) TEC-AS-P-006	MAX 0.5	0.3
VISCOSITY @25° C	CPs	JIS K 7233(86)	4,000 ~ 12,000	9,400
NON-VOLATILE CONTENT	wt%	TEC-AS-P-012	74 ~ 76	75.39



Quality - Responsibility - Stewardship

